

Electrically Conductive Anti-Fatigue Mats

Specification Sheet



Performance	Best
Uses	Dry areas at risk for damage from static electricity
Compound	Vinyl / SBR Rubber
Coefficient of Friction	0.68 / 0.78 Dry per ASTM F1677
Tabor Abrasion	1% lost @ 1,000 cycles per Fed. Std. 191
Flammability	"A" Rating per MVSS 302
Warranty	3 years
Anti-Fatigue Value	4.5
Wear Resistance	4.5
Conductivity	4
MNF	70
Thickness	9/16" & 1"
Resistivity	RTT: 1×10^6 to 8×10^6 Ohms