

152 Rollins Avenue #102 Rockville, MD 20852 800-762-9010 240-780-3309 (fax) http://www.floormats.com

Everlast Rubber Runners

COMPOSITION:	Recycled Rubber – 97% Urethane Binders- 3%				
THICKNESS / WEIGHT: (Nominal)	3/8" (2.0 to 2.2 lbs./sq. ft.) 1/4" (1.6 lbs./sq. ft.)				
SURFACES	Flat One Side Wire Mesh Texture, Anti-Skid Surface on opposite side Both Sides Non-Porous				
COLOR:	Black or Black with flecks of colored EPDM rubber				
TENSILE STRENGTH:	350 psi				
HARDNESS:	60-64 Shore A				
FLAMMABILITY:	Passes Federal Flammability Standard Doc FF 1-70 CPSC				
DIMENSIONAL STABILITY:	+0.242% at two hours @ 60°C -0.092% at 48 hours @ 20°C & 65% Rel. Humidity				
ULTIMATE ELONGATION:	ASTM D412 on 1/8"	83 %			
FLAME SPREAD:	(UL 94 Standard, Horizontal Burning Test for Classifying Material 94HB)	0.495"/MIN on 3/4" thick mat			
CRITICAL RADIANT FLUX:	ASTM E648-94a	0.11 watts/sq. cm			
ELECTRICAL RESISTANCE:	ASTM D991	1.6 x 10 ⁹ megohms average 5.6 x 10 ⁸ megohms average			
ELECTROSTATIC PROPENSITY:	AATCC Test Method 134- 1991	NEG 0.9 KV Maximum Voltage			
THERMAL RESISTANCE:	R-Value	1/4": 0.18 3/8": 0.36			
THERMAL RESISTIVITY:	0.72 (all thicknesses)				

THERMAL CONDUCTIVITY:	K-Value	1.39 (all thicknesses)			
TEAR RESISTANCE (ppi):	ASTM D624	150			
COEFFICIENT OF FRICTION:	ASTM D1894	0.96			
DENSITY (lb/ft³):	ASTM D3676	64.6			
COMPRESSION & RECOVERY:	ASTM D575	Immediate 98.1% After 24 hours 99.2% After 48 hours 99.4% After 72 hours 99.7% After 96 hours 99.7%			
ACCELERATED WEATHERING: Carbon Arch Weather-ometer	Fed-Std-191 Method 5804 except with filters removed for the test	Tensile, psi Elongation, %	Unexposed 499 145	Full Exposure 344 70	

All testing is conducted off site by esteemed independent testing institutions. Copies of actual testing reports